

TECHNICAL DATA SHEET

Wind Insulation PAROTEC vinto

Wind barrier for installation under exterior wall facade systems. Protection against moisture and air penetration.

Length	EN 1848-2	50 m (-0%)
Width	EN 1848-2	1,5 m (-0%)
Straightness	EN 1848-2	pass
Mass per unit area	EN 1849-2	100g/m ² (± 10%)
Reaction to fire	EN 11925-2	class F
Resistance to water penetration	EN 1928	class W3
Tensile strength along	EN 12311-1	240 ±90 (N/50 mm)
Tensile strength across	EN 12311-1	160 ±90 (N/50 mm)
Elongation at max tensile along	EN 12311-1	≤ 80%
Elongation at max tensile across	EN 12311-1	≤ 80%
Tear resistance along	EN 12310	100 ±90 (N)
Tear resistance across	EN 12310	100 ±95 (N)
Flexibility at low temperature	EN 1109	-30°C
Water vapour transmission properties	EN 12572/C	0,02 m (+0,019 m)
Resistance to water penetration - after aging	EN 1928	class W3
Windproof insulation	EN 12114	<0,06 m ³ /m ² h 100Pa
Elongation at max tensile along - after aging	EN 12311	<80%
Elongation at max tensile across - after aging	EN 12311	<80%
Tensile strength across - after aging	EN 12311	<30%
Tensile strength along - after aging	EN 12311	<30%

On behalf of the producer signed by:
Tomasz Staszewski



Batorowo 05.11.2024